

# Performance of iron-functionalized activated carbon catalysts (Fe/AC-*f*) on CWPO wastewater treatment

S. Mesa<sup>1</sup>, A. Rey<sup>2</sup>, C. J. Duran-Valle<sup>3</sup>, A. Bahamonde<sup>1</sup> and M. Faraldos<sup>1\*</sup>

<sup>1</sup>Instituto de Catálisis y Petroleoquímica, CSIC, C/ Marie Curie 2, 28049 Madrid (Spain).

<sup>2</sup>Dpto. de Ingeniería y Química Física, Universidad de Extremadura, Avd. Elvas S/N, 06006 Badajoz (Spain).

<sup>3</sup>Dpto. de Química Orgánica e Inorgánica and IACYS, Universidad de Extremadura, Avd. Elvas S/N, 06006 Badajoz (Spain).

\* Correspondence: mfaraldos@icp.csic.es

## Supplementary Information.

### Tables:

**Table S1.** Catalysts nomenclature and characteristics

### Figures:

Figure S1 – XRD of Fe/AC-*f* catalysts: a) Fe/CM-*f* catalysts and b) Fe/CN-*f* catalysts

Figure S2 – N<sub>2</sub> isotherms of Fe/AC-*f* catalysts: a) Fe/CM-*f* catalysts and b) Fe/CN-*f* catalysts

**Table S1.** Catalysts nomenclature and characteristics

| Treatment       | Support | $V_{\text{Fe(NO}_3)_3}$<br>( $\text{mL} \cdot \text{g}_{\text{support}}^{-1}$ ) | Catalysts | Fe (%) | T <sub>calcination</sub> (°C) |
|-----------------|---------|---------------------------------------------------------------------------------|-----------|--------|-------------------------------|
| -               | CM      | 0.88                                                                            | Fe/CM     | 4      | 250                           |
|                 | CN      | 0.91                                                                            | Fe/CN     |        |                               |
| Sulfuric acid   | CM-A    | 1.03                                                                            | Fe/CM-A   | 4      | 250                           |
|                 | CN-A    | 1.17                                                                            | Fe/CN-A   |        |                               |
| Nitric acid     | CM-O    | 0.97                                                                            | Fe/CM-O   | 4      | 250                           |
|                 | CN-O    | 1.10                                                                            | Fe/CN-O   |        |                               |
| Ethylenediamine | CM-B    | 0.81                                                                            | Fe/CM-B   | 4      | 250                           |
|                 | CN-B    | 0.67                                                                            | Fe/CN-B   |        |                               |




Figure S1 – XRD of Fe/AC-*f* catalysts: a) Fe/CM-*f* catalysts and b) Fe/CN-*f* catalysts




Figure S2 – N<sub>2</sub> isotherms of Fe/AC-*f* catalysts: a) Fe/CM-*f* catalysts and b) Fe/CN-*f* catalysts