

Phase transition behavior of the layered perovskite $\text{CsBi}_{0.6}\text{La}_{0.4}\text{Nb}_2\text{O}_7$: a hybrid improper ferroelectric

Charlotte A. L. Dixon¹, Jason A. McNulty¹, Kevin S. Knight^{2,3}, Alexandra S. Gibbs⁴ and Philip Lightfoot^{1,*}

Supplementary Material

Synthesis: The $\text{CsBi}_{1-x}\text{La}_x\text{Nb}_2\text{O}_7$ solid solution (for $0 < x < 1$, in 0.1 increments) was synthesised using traditional ceramic methods. Stoichiometric amounts of La_2O_3 (99.9 % Sigma-Aldrich), Nb_2O_5 (99.9 % Alfa Aesar) and a 20 % excess of Cs_2CO_3 (99 % Alfa Aesar) were dried at 100 °C for 24 hours. The loose powders were ground for a period of 30 minutes and pressed into pellets of approximately 10 mm diameter and 5 mm thickness. The pellets were annealed at 1000 °C for a period of 24 hours with a cooling rate of 10 °min⁻¹.

Powder Diffraction: X-ray powder diffraction was carried out using a PANalytical Empyrean diffractometer (Cu $K_{\alpha 1}$ radiation source). Diffraction patterns were collected over the 2θ range $3 \leq 2\theta \leq 70$ °C and a collection time of 1 hour. Analysis using Rietveld refinement methods of the resulting diffraction patterns was carried out with the GSAS software package and EXPGUI interface.

The Rietveld refinement models used were the $P2_1am$ model for $0 < x \leq 0.5$ and the parent $P4/mmm$ model for $x > 0.5$. For the $x > 0.5$ compositions we acknowledge that although the unit cells are *metrically* tetragonal, within the resolution of our instrumentation, the true symmetry is likely to be the $Amm2$ model reported for $\text{CsLaNb}_2\text{O}_7$. This approximation has negligible influence on the lattice parameters reported here, which are intended only to demonstrate that a continuous solid solution exists, and that the composition $\text{CsBi}_{0.6}\text{La}_{0.4}\text{Nb}_2\text{O}_7$ targeted here is validated experimentally, in the absence of precise chemical analysis.




Figure S1: a) normalised a (black squares) and b (red circles) lattice parameters obtained for varying values of x across the solid solution $\text{CsBi}_{1-x}\text{La}_x\text{Nb}_2\text{O}_7$, b) c lattice parameter for varying values of x and c) (normalized) unit cell volume for varying values of x .