



## 3D Flower-like Tin Monosulfide/Carbon Nanocomposite Anodes for Sodium-Ion Batteries

Changju Chae <sup>1</sup> and Sunho Jeong <sup>2,\*</sup>


<sup>1</sup> Division of Advanced Materials, Korea Research Institute of Chemical Technology (KRICT), Daejeon 34114, Korea; changju@kRICT.re.kr

<sup>2</sup> Department of Advanced Materials Engineering for Information and Electronics, Integrated Education Institute for Frontier Science & Technology (BK21 Four), Kyung Hee University, Yongin-si, 17104, Korea


\* Correspondence: sjeong@khu.ac.kr

**Table S1.** The values in coulombic efficiency for the cell employing RGO/F-SnS NCs active materials.


Cycle #	Coulombic Efficiency
1st	32.1%
2nd	101.5%
3rd	94.1%
4th	94.9%
5th	95.5%
6th	95.9%
7th	96.0%




**Figure S1.** Cyclic voltammetry data for the cell employing the F-SnS NPs active materials.



**Figure S2.** Cyclic voltammetry data for the cell employing the RGO/F-SnS NCs active materials.



**Figure S3.** Voltage profiles for the cell employing the RGO/F-SnS NCs active materials. The current density was 200 mA/g.



**Figure S4.** (a) Cyclability and (b) electrochemical impedance spectroscopy data during long-term cycling test for the cell employing the RGO/F-SnS NCs active materials. The current density was 200 mA/g.