

Supporting information

**Solar-light-induced photocatalytic response of BiOCl/PANI composite
towards the degradation of tetracycline**

Janis Goyal[†], Surbhi Sharma[†] and Soumen Basu^{*}

School of Chemistry and Biochemistry, Thapar Institute of Engineering & Technology, Patiala-147004, India.

^{}Corresponding author: E-mail:soumen.basu@thapar.edu*

[†]These authors contributed equally to this work.

Table S1. Parameters for Rh-B and TC degradation using different materials.

Materials	Rhodamine-B (Rh-B)		Tetracycline (TC)	
	% Degradation	Rate constant (min ⁻¹)	% Degradation	Rate constant (min ⁻¹)
No catalyst	16	0.0015	9	0.0018
BiOCl	60	0.0056	38	0.0048
PANI	72	0.0107	52	0.0058
TiO ₂	44	0.0056	34	0.0037
PB15	97	0.0236	77	0.0106




Figure S1. Plot of pzc measurement of Rh-B